

Material	HRA
1045 AR	59
1045 Quenched	77
1045 Q & T 250C	75
1045 Normalized	54
4010 Oil quenched	75.5
1045 Oil quenched	77
Charpy	Foot pound
1045 Quenched	2
1045 temp 20-min 250 C	4
1045 AR	37